


Galden PFPE: Reliability Testing Fluids

Product Data Sheet

Galden fluids are low molecular weight perfluoropolyether (PFPE) fluids having the general chemical structure of:



PFPEs have exceptional thermal and oxidative stability, as well as extreme chemical inertness. Their non-reactivity, high dielectric strength, low toxicity, non-flammability and non-solvent features make PFPEs ideal for electronic reliability testing including thermal shock and hermetic seal testing.

All Galden grades are:

- Environmentally safe-do not damage the ozone
- Highly inert
- Good heat transfer medium
- Chemically and thermally resistant
- Non-toxic



Typical Properties

Typical Property	Units	DET	D/80	D/100	D02	D02-TS	D03	D05
Boiling Point	°C (°F)	91 (196)	84 (183)	104 (219)	175 (347)	165 (329)	200 (392)	230 (446)
Pour Point	°C (°F)	-110 (-230)	-79 (-110)	-103 (-217)	-97 (-143)	-97 (-143)	-85 (-121)	-77 (-107)
Density, 25°C	g/Cm ³ (lb./ft ³)	1.70 (1.70)	1.73 (108.0)	1.77 (110.4)	1.77 (110.5)	1.77 (110.5)	1.79 (111.7)	1.82 (113.6)
Density, -54°C	g/Cm ³ (lb./ft ³)	1.85 (1.85)	1.93 (120.6)	1.96 (122.7)	1.95 (121.7)	1.95 (121.7)	1.96 (122.4)	1.98 (123.6)
Kinematic Viscosity, 25°C	cSt	0.60	0.55	0.81	1.8	1.8	2.4	4.4
Kinematic Viscosity, -54°C	cSt	6.0	5.3	9.1	65	45	160	1100
Vapor Pressure, 25°C	Torr (lb/in ²)	57 (1.10)	79 (1.53)	35 (0.67)	<1 (<0.02)	<1 (<0.02)	<1 (<0.02)	<1 (<0.02)
Specific Heat, 25°C	cal/g·°C (Btu/lb·°F)	0.23 (0.23)	0.23 (0.23)	0.23 (0.23)	0.23 (0.23)	0.23 (0.23)	0.23 (0.23)	0.23 (0.23)
Heat of Vaporization @Boiling Point	cal/g (Btu/lb)	17 (31)	19 (35)	20 (36)	17 (31)	17 (31)	15 (27)	15 (27)
Thermal Conductivity, 25°C	Watts/cm°C (Btu/lb-ft°C)	0.0007 (0.041)	0.0006 (0.035)	0.0006 (0.035)	0.0007 (0.041)	0.0007 (0.041)	0.0007 (0.041)	0.0007 (0.041)
Coefficient of Expansion	Cm ³ (cm ³) (°C), (ft ³ (ft ³)(°F))	0.0011 (0.0007)	0.0014 (0.0008)	0.0014 (0.0008)	0.0011 (0.0007)	0.0011 (0.0006)	0.0011 (0.0007)	0.0011 (0.0007)
Surface Tension, 25°C	dynes/cm (poundals/in)	16 (0.0029)	17 (0.0031)	16 (0.0029)	17 (0.0033)	18 (0.0031)	19 (0.0035)	20 (0.0037)

continued on page 2

For information contact your Solvay Solexis representative or:

Europe

Solvay Solexis S.p.A. (Italy)

Tel: +39-02-3835-1

Fax: +39-02-3835-2129

Email: solvaysolexis.ita@solvay.com

North America

Solvay Solexis, Inc.

Tel: +1-856-853-8119

Fax: +1-856-853-6405

Email: solvaysolexisinfo@solvay.com

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Solexis, Inc. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes.

Trademarks and/or other Solvay Solexis, Inc. products referenced herein are either trademarks or registered trademarks of Solvay Solexis, Inc. or its affiliates.

Copyright 2004, Solvay Solexis, Inc. All Rights Reserved.

Galden PFPE: Reliability Testing Fluids

Product Data Sheet

Typical Properties (continued)

Typical Property	Units	DET	D/80	D/100	D02	D02-TS	D03	D05
Dielectric Strength, 25°C	KV- 2.54mm gap (KV- 0.10in gap)	40 (40)	40 (40)	40 (40)	40 (40)	40 (40)	40 (40)	40 (40)
Dielectric Constant 25°C (1Khz)	—	1.90	1.80	1.80	1.90	1.90	1.94	1.94
Dissipation Factor 25°C (1Khz)	—	2x10 ⁻⁴	3x10 ⁻⁴	3x10 ⁻⁴	2x10 ⁻⁴	2x10 ⁻⁴	2x10 ⁻⁴	2x10 ⁻⁴
Volume Resistivity, 25°C	Ohm-cm	1x10 ¹⁵	1x10 ¹⁵	1x10 ¹⁵	6x10 ¹⁵	6x10 ¹⁵	6x10 ¹⁵	6x10 ¹⁵
Solubility of Water	Ppm(wt.)	14	15	13	14	14	14	14
Solubility of Air	Cm ³ gas/100Cm ³ liquid	26	45	41	26	26	26	26
Average Molecular Weight	a.m.u.	400	390	416	760	760	870	1020

Thermal Shock Testing

Thermal Shock testing is conducted to determine the resistance of a device to extreme temperature changes. The test is carried out by alternately immersing the devices in liquid baths maintained at two different temperatures, as specified in MIL STD 883, Method 1011, or MIL STD 202, Method 107.

Traditionally, 2 different fluids were used in both the hot and cold baths. This practice, while conforming to the MIL STD, presents the following problems: high fluid loss from the cold bath; cross contamination between the hot and cold baths; extensive machine down time; and dual fluid inventory.

Single Fluid = Lower Costs

Galden D02TS is a single fluid which replaces the dual fluid system. D02TS meets the MIL STDS 883 and 202

for both the hot and cold baths. The single fluid solution allows for a dramatic decrease in operating costs by:

- Decreasing fluid consumption
- Reducing machine downtime
- Eliminating cross contamination
- Reducing inventory to a single fluid

For use in condition D, E or F, the following military approved GALDEN fluids can be used:

Condition D - D05/D100, D80

Condition E (Hot test) - D02

Condition F (Hot test) - D05

For information contact your Solvay Solexis representative or:

Europe

Solvay Solexis S.p.A. (Italy)

Tel: +39-02-3835-1

Fax: +39-02-3835-2129

Email: solvaysolexis.ita@solvay.com

North America

Solvay Solexis, Inc.

Tel: +1-856-853-8119

Fax: +1-856-853-6405

Email: solvaysolexisinfo@solvay.com

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Solexis, Inc. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes.

Trademarks and/or other Solvay Solexis, Inc. products referenced herein are either trademarks or registered trademarks of Solvay Solexis, Inc. or its affiliates.

Copyright 2004, Solvay Solexis, Inc. All Rights Reserved.

Galden PFPE: Reliability Testing Fluids

Product Data Sheet

Approved Galden Fluids for Liquid Thermal Shock Testing MIL STD 883 - 1011

Condition	Hot step (°C)	Cold step (°C)	Hot bath	Cold Bath
B	+10 125 -0	+0 -55 -10	D02 D02TS	D/80 D02TS D100
C	+10 150 -0	+0 -65 -10	D02 D02TS	D/80 D02TS D100
D	+10 200 -0	+0 -65 -10	D05	D/80 D100
E	+10 150 -0	+5 -195 -10	D02 D02TS	Liquid N ²
F	+10 200 -0	+5 -195 -10	D05	Liquid N ²

Hermetic Seal Testing

To guarantee the hermeticity of sealed devices, a leak test procedure as defined by MIL STD 883, Method 1014, MIL STD 750, Method 1071, or MIL STD 202, Method 112 is performed.

Galden®

For information contact your Solvay Solexis representative or:

Europe
Solvay Solexis S.p.A. (Italy)
Tel: +39-02-3835-1
Fax: +39-02-3835-2129
Email: solvaysolexis.ita@solvay.com

North America
Solvay Solexis
Tel: +1-856-853-8119
Fax: +1-856-853-6405
Email: solvaysolexisinfo@solvay.com

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Solexis, Inc. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes.

Trademarks and/or other Solvay Solexis, Inc. products referenced herein are either trademarks or registered trademarks of Solvay Solexis, Inc. or its affiliates.

Copyright 2004, Solvay Solexis, Inc. All Rights Reserved.

Galden PFPE: Reliability Testing Fluids

Product Data Sheet

Specific physical property requirements have been defined in 883 for detector and indicator fluids:

Physical Property Requirements of Perfluorocarbon Fluids Defined in Test Method 1014.9 (notice 8)

Property	Type I	Type II	Type III	ASTM Test Method
Boiling Point (°C)	50-95	140-200	50-110	D1120
Surface Tension (dynes/cm) @25°C	—	<18	—	D971, D1331
Density @25°C (gm/ml)	>1.6	>1.6	>1.6	D941
Density @125°C (gm/ml)	—	>1.5	—	D941
Dielctric Strength (volts/mil)	>300	>300	>300	D877
Residue (µgm/gm)	>50	>50	>50	D2109
Appearance	Clear Colorless Liquid			

Galden DET: Detector Fluid Specifically Designed for Vapor Detection Systems

- Type I fluid that meets the requirements of MIL-STD 883
- Lower consumption with respect to traditionally used Type I approved products
- Higher reliability as the result of both low and high boiling point components in the fluid
- High boiling point components enter the devices via the large leaks and remain liquid until the test is performed
- Low boiling point components penetrate into the small leaks
- Tested and approved by the major equipment manufacturer of Vapor Detection Systems

Galden DET can also be used in bubble test equipment as a detector fluid.

Galden D02: A Low Consumption Indicator Fluid

- Higher boiling point, reducing evaporative loss
- Lower liquid density than competitive fluids, reducing operating costs
- Lower vapor pressure at test temperature, minimizing fluid loss

Galden D03: A Lower Cost Indicator Fluid for Non Military Applications

- Lower consumption compared to other commercially available indicator fluids

To complete the product offering, Solvay Solexis also offers MIL-STD approved Galden D/80, a Type I detector fluid and Galden D/100, a Type III detector fluid.

GALDEN®

For information contact your Solvay Solexis representative or:

Europe

Solvay Solexis S.p.A. (Italy)

Tel: +39-02-3835-1

Fax: +39-02-3835-2129

Email: solvaysolexis.ita@solvay.com

North America

Solvay Solexis

Tel: +1-856-853-8119

Fax: +1-856-853-6405

Email: solvaysolexisinfo@solvay.com

To our actual knowledge, the information contained herein is accurate as of the date of this document. However, neither Solvay Solexis, Inc. nor any of its affiliates makes any warranty, express or implied, or accepts any liability in connection with this information or its use. This information is for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. The user alone must finally determine suitability of any information or material for any contemplated use, the manner of use and whether any patents are infringed. This information gives typical properties only and is not to be used for specification purposes.

Trademarks and/or other Solvay Solexis, Inc. products referenced herein are either trademarks or registered trademarks of Solvay Solexis, Inc. or its affiliates.

Copyright 2004, Solvay Solexis, Inc. All Rights Reserved.